



PART NUMBERS

330970 (1) 36" x 75' Roll

FEATURES AND BENEFITS

- TPO backing with proven exterior performance
- Aggressive grip & adhesion
- Ideal adhesive/sealant thickness
- Immediate leak proof results
- Easy, fast application
- Stays flexible
- Installs onto ductwork or over rigid foil-faced insulation

SPECIFICATION/STANDARDS COMPLIANCE

Property	Method	Results
EPDM Sheet Used in Single-Ply Roof Membrane	ASTM D4637 Program # 9	Pass
Tensile Strength	ASTM D882	700 psi avg.
Elongation	ASTM D882	900% avg.
Tear Resistance	ASTM D1922	600 grams avg.
U.V. Resistance	ASTM D4637	3,000 hours, Pass. No change (Degradation @ 0.70 W/m ² @ 340 nm wavelength, 176°F (80°C) black body temperature)

TYPICAL PROPERTIES AND CHARACTERISTICS

Appearance	White (non-gloss) TPO (Thermoplastic Polyolefin) exterior with gray sealant
Sealant Material	Elastomeric Modified Butyl Rubber The Gray Matter™
Thickness	22 mils
Peel Strength	≥10 lbs. per linear inch
Flexibility (low temp)	Passes, no cracking
Bonding Time	Immediate, water tight, aggressive grip. Full bond within 24 hours.
Service Temperature	-40°F to 180°F (-40°C to 82°C)
Water Resistance	Excellent. Surface must be clean and dry before application.

APPLICATION

Temperature	35°F to 110°F (1.7°C to 44°C)
Preparation	Surface must be dry and free of dirt, oil, and grease.
Method	Position the product precisely. Product is not repositionable. DO NOT STRETCH. Remove the release liner and press down firmly starting at center and working toward outside edge while removing trapped air. Edges shall be firmly adhered to the substrate without opening or fishmouths. Roll or squeegee surfaces to maximize adhesion.
Clean Up	Un-Tack™ or solvent (Use safe handling practices.)

PRECAUTIONS

Surface must be clean and free of moisture, contamination, and foreign matter. Keep out of the reach of children.

For Industrial Professional Use Only.

STORAGE

Temperature	35°F to 110°F (1.7°C to 44°C)
Shelf Life	24 months